

FLASH

Fast Dry, Rapid Recoat Floor Sealer/Finish

Flash is formulated from a unique combination of the latest polymers and drying aids to create this time saving floor sealer and finish. Flash can be recoated in as soon as 10 minutes after the previous coat has been applied. This means as much as a 30 minute time savings per coat when compared to normal sealers and finishes. This allows high traffic, critical function areas to be coated and put back into service in 1/3 the amount of time that is normally required. The low odor formula makes it a great choice for hospitals, retailers, lobbies, and any area where indoor air quality is a concern.



APPLICATION & MAINTENANCE

Best results are obtained when the finish is applied to floor surfaces that are 60° F. or warmer.

- Remove old finish or wax with one of Perma's premium quality strippers.
- Vacuum or mop up the stripping solution. If an alkaline stripper was used, rinse the floor thoroughly using 1 ounce of #127 Tops or Easy Mix 1005 Neutral (1:128) per gallon of clean water.
- When used as a fast dry sealer and base for other finishes a minimum of 2 coats is recommended to obtain appropriate build.
- To obtain an acceptable level of appearance and gloss, when used as a fast dry sealer/finish a minimum 3 coats of finish is required. Optimum appearance and gloss will be obtained by applying 4-6 coats, depending on the porosity and type of flooring.
- Apply thin even coats, allowing the finish to dry depending on humidity and temperature for approximately 10 minutes between coats.
- To recoat, scrub the floor with a low speed (175-300 Rpm) buffing machine or automatic scrubber equipped with a blue or green scrubbing pad and a solution of #127 Tops Neutral Cleaner or #129 Super Blue for heavier soil conditions and allow it to dry. To remove a partial coat of floor finish and reduce finish build up a maroon surface preparation pad may also be used.
- Apply thin even coats, allowing the finish to dry for approximately 10 minutes between coats.
- For daily maintenance, sweep and/or dry mop.
- Daily damp mop floors with Tops or Easy Mix 1005 Neutral Cleaner
- Use Jump Start Maintainer or Easy Mix 1035 for high speed burnishing or One Step Spray Buff for standard speed buffers to restore finish gloss.

SPECIFICATIONS

Nonvolatile Solids	22 ± 0.6%
Total Active	27%
pH	8.1 - 8.9
Gloss 60°	89 @ 5 coats
Color	White Milky Emulsion
Weight Per Gallon	8.55 - 8.65
Slip Resistance (ASTM)	0.5 minimum
Stability	1 year minimum at room temperature
Freeze/Thaw Stability	3 cycles minimum
Drying Time	10-15 minutes
Water Resistance	Excellent
Gallon Coverage (Feet ²)	2000 ± 10%
Removability (Gardner)	75 cycles maximum
Durability (ASTM D-968)	3,680 grams

SAFETY INFORMATION

Health	1
Flammability	0
Reactivity	0
Personal Protection	B

This material is not a hazardous mixture as defined in 29 CFR 1919, 1200 and M.G.L. c. 111F. Safety glasses and gloves should be worn during application and handling. If ingested, give one or two glasses of milk or water. In the event of eye contact, flush area with water for 15 minutes. **Consult with a physician.** Contains Glycol Ethers. For detailed information, consult MSDS sheet.



605 Springs Road, Bedford, MA 01730 USA
Tel: 978.667.5161, Fax: 978.670.5797
E-mail: Info@perma.com
www.perma.com